

**IMUTHANE**
CASTABLE POLYURETHANE
ELASTOMERS
32-95A**IMUTHANE**
32-95A

IMUTHANE 32-95A is a TDI / PPG based prepolymer which yields 95/48 Shore-D elastomer when cured with 4, 4' methylene bis ortho chloroaniline (MBOCA).

Typical Prepolymer Properties

% NCO	5.8 – 6.2
Brookfield Viscosity @ 100° C	0.5 – 2.0
Specific Gravity @ 77° F (25° C)	1.08
@ 212° F (100° C)	1.02

Typical Process Conditions

IMUTHANE 32-95A, °F (°C)	140 (60)
MBOCA, °F (°C)	240 (115)
Mold, °F (°C)	212 (100)
% Theory	90
Pot Life, min	4
Cure Time, min @ °F (°C)	60 @ 212 (100)
Post Cure, hrs @ °F (°C)	16 @ 158 (70)

Typical Physical Properties

Shore Hardness	95A/48D
100% Modulus, psi (MPa)	1850 (10.3)
300% Modulus, psi (MPa)	3400 (17.2)
Tensile, psi (MPa)	4700 (27.6)
Elongation, %	325
Tear Strength, Die C, pli (kN/m)	450 (65.7)
Tear Strength, (D470), pli (kN/m)	120 (14.0)
Bashore Rebound, %	48
Compression Set, Method B, 22 hrs @ 158°F (70°C), %	35
Specific Gravity	1.13

The data contained herein are believed to be reliable. However, there is no guarantee that the same results will be obtained under different conditions. Fit for use testing should be conducted by each user.